



PPC MF-300 NB

Product Technical Data Sheet

Categories : Polymer, Polypropylene

Information: Impact modified, medium flow, olefin based no break copolymer

Form: Pellets

Appearance: Black

Method: Injection molding

PROPERTY	UNITS	TYPICAL VALUE	TEST METHOD
PHYSICAL			
Density	g/cc	0.90	D 792
Melt Flow Rate	g/10 min.	10–15	D 1238 230 C/2.16 kg
MECHANICAL			
Tensile Strength	PSI	2200	D 638
Flex Modulus	KSI	120	D 790
Izod, Impact, notched	Ft–lb/in	8+	D 256
THERMAL			
HDT at 66 PSI	Deg F	200	D 648
HDT at 264 PSI	Deg F	120	D 648

LEGAL DISCLAIMER

The information presented here is, to the best of our knowledge and belief, accurate and reliable. Because conditions of use are beyond our control, we make no warranties, expressed or implied and specifically exclude any and all warranties of merchantability and fitness for a particular purpose. Our products are sold with the express understanding that our customers will conduct their own tests to determine the suitability of the material for their particular use. Nothing herein shall be construed as permission or recommendation to practice a patented invention without a license. The sole liability of Polymer Technologies, Inc. for any claims arising out of the manufacture, use or sale of its products shall be for our customers purchase price or material replacement.